



USA 120S-1 Welding Wire and Rod



Arc-Zone.com

WASHINGTON ALLOY'S Quality Management System is Certified to ISO 9001:2008
Cert # 05-R0925

ALLOY DESCRIPTION AND APPLICATION;

USA 120S-1 is used for a variety of steels where high strength and ductility are critical. It is designed to give high notch toughness, yield strength and impact resistance. USA 120S-1 can be welded at an interpass temperature as low as 300°F while also offering high ductility to -75°F. Typical application may be high yield steels such as T-1, HY-100 and other steels in the 100,000 psi YS class, pressure vessels. Mechanical properties from the weld deposit will vary depending on heat input used. Preheat and interpass of 300°F may be required.

TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	75/25 CO ₂ (cfh)
0.023	80-350	30-85	14-19	10-15	20-25
0.030	110-340	40-130	15-20	12-24	20-25
0.035	100-520	60-235	16-25	11-40	20-30
0.045	70-270	90-290	18-23	12-22	25-35
<i>Spray</i> 0.035	320-600	160-300	23-26	11-22	⁽¹⁾ 25-35
0.045	170-550	170-375	23-29	12-21	⁽¹⁾ 25-35
1/16"	175-350	275-475	25-31	9-19	⁽¹⁾ 25-35

TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	100-160	12	3/8"	20	1/16-3/32"
1/16-3/32"	3/32"	120-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	150-300	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	120S-S-1		AWS Spec.	Typical
Carbon	0.10 max	0.070	Tensile Strength (psi)	120,000 min.	125,000
Manganese	1.40-1.80	1.55	Yield Strength (psi)	105,000 min.	110,000
Silicon	0.25-0.60	0.35	Elongation in 2"	14% min.	15%
Phosphorus	0.010 max	0.006	Charpy V-notch at -60°F	50 ft-lbs min.	70 ft-lbs
Sulfur	0.010 max	0.008			
Nickel	2.00-2.80	2.40	AWS maximum as follows : Ti, Zr, Al = 0.10 each &		
Molybdenum	0.30-0.65	0.55	V = 0.03 : Cu = 0.25		
Chromium	0.60 max	0.45			

AVAILABLE SIZES: TC 120S-1= Spools of .035, .045, 1/16, 3/32

TT 120S-1 = Cut lengths of .035, .045, 1/16, 3/32, 1/8

SPECIFICATIONS; ANSI/AWS A5.28 ER 120S-1

ASME SFA 5.28 ER 120S-1

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.



Arc-Zone.com, Inc.

760-931-1500 – sales@arc-zone.com

2091 Las Palmas Drive, Ste. F – Carlsbad, CA 92011-1551 - USA